

MMA STICKELECTRODE (STAINLESS STEEL)



			WELDING WIRE CHEMICAL COMPOSITION (%)								
Model	Packaging (Kg/Box)	Size (mm)	C	MN	SI	P	S	CR	NI	MO	CU
Stainless Steel 308	5	2.5 - 5	0.01	0.61	1.02	0.03	0.02	19.34	10.54	0.18	0.32

				MECHANICAL PROPERTIES OF DECOMPOSITION METAL							
Model	Yield Strength (Mpa)	Tensile Strength (Mpa)	Elaongation (%)								
Stainless Steel 308	600	450	40								

			WELDING WIRE CHEMICAL COMPOSITION (%)								
Model	Packaging (Kg/Box)	Size (mm)	C	MN	SI	P	S	CR	NI	MO	CU
Stainless Steel 309	5	2.5 - 5	0.31	0.9	0.71	0.02	0.03	23.08	12.61	0.13	0.44

				MECHANICAL PROPERTIES OF DECOMPOSITION METAL							
Model	Yield Strength (Mpa)	Tensile Strength (Mpa)	Elaongation (%)								
Stainless Steel 308	530	400	37								

			WELDING ELECTRODES CHEMICAL COMPOSITION (%)								
Model	Packaging (Kg/Box)	Size (mm)	C	MN	SI	P	S	CR	NI	MO	CU
Stainless Steel 316	5	2.5 - 5	0.03	0.7	0.89	0.03	0.04	17.18	11	2.94	0.31

				MECHANICAL PROPERTIES OF DECOMPOSITION METAL							
Model	Yield Strength (Mpa)	Tensile Strength (Mpa)	Elaongation (%)								
Stainless Steel 316	610	400	38								



Singapore HQ
Blk 6 Marsiling Industrial Estate Road 1
#01-14 Singapore 739275

Showroom
No. 3 Soon Lee Street, Pioneer
Junction #01-37 Singapore 627606

Myanmar
Building I, Room 37/38
Thiri Yadanar Retail/Wholesale Market North
Okkalapa Township, Yangon Division Myanmar